

LAW OFFICES

ALIX, YALE & RISTAS, LLP

(FORMERLY CHILTON, ALIX & VAN KIRK)

750 MAIN STREET

HARTFORD, CONNECTICUT 06103-2721

(860) 527-9211

JAMES E. ALIX
GUY D. YALE
L. JAMES RISTAS
RICHARD H. BERNHEIM
CLIFFORD P. KELLY
JAMES E. PIOTROWSKI
THOMAS J. MENARD
BENJAMIN Y. AGRESTA

OF COUNSEL

RALPH H. CHILTON

ROGER A. VAN KIRK

PATENT, TRADEMARK,
COPYRIGHT AND
COMPUTER LAW

FACSIMILE
(860) 527-5029
E-MAIL
ayrlp@pcdlaw.com

FACSIMILE TRANSMISSION

April 4, 2003

*O.K. to enter
file
4-03*

To: Examiner M. Alvo
Group Art Unit 1731
United States Patent and Trademark Office

Re: **United States Patent Application No. 08/907,687**
Title: Method of Pretreating Lignocellulose Fiber-Containing
Material for the Pulp Making Process
Inventor: Marc J. Sabourin
Our Ref.: ANDR/346/US

FAX: (703) 872-9065

FROM: L. James Ristas

MESSAGE: Attached please find an Amendment After Filing Of Applicant's Appeal Brief

AFTER FILING
Appeal Brief 99

NUMBER OF PAGES BEING TRANSMITTED 11 page(s) including cover sheet.

IF YOU DO NOT RECEIVE ALL PAGES OR ARE HAVING TROUBLE,
PLEASE CONTACT ALIX, YALE & RISTAS, LLP IMMEDIATELY AT 527-9211
AND ASK FOR DAHLIA STEELE

CONFIRMATION COPY TO FOLLOW: ☐ Yes ☒ No

The information contained in this telecopy message is intended only for the use of the individual or entity named and may contain information that is privileged, confidential and exempt from disclosure under applicable law. If the reader of this message is not the intended recipient, or the employee or agent responsible for delivering it to the intended recipient, you are hereby notified that any dissemination, distribution or copying of this communication is strictly prohibited. If you have received this message in error, please immediately notify us by telephone and return the original message to us at the above address via the U.S. Postal Service. Thank you.

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re patent application of: Marc SABOURIN

Application No.: 08/907,687

Examiner: M. Alvo

Filing Date: August 8, 1997

Group Art Unit: 1731

For: **METHOD OF PRE-TREATING LIGNOCELLULOSE FIBER CONTAINING
MATERIAL FOR THE PULP MAKING PROCESS**

#H/BM
36/4-7-03

**Commissioner for Patents
Washington, DC 20231**

Sir:

**AMENDMENT AFTER FILING OF APPLICANT'S APPEAL BRIEF
(FILING BY FAX ONLY)**

As a result of the telephone interview initiated by Examiner Alvo on April 3, 2003, applicant hereby submits an amendment to the description and claims, and requests entry thereof for purposes of reconsideration and allowance of the application:

In the Description


Replace the paragraph spanning page 1, line 9 to page 2, line 1, of the Background portion of the Specification including the indicated [deletions] and additions relative to the text as pending as of the Appeal on 01/21/03:

Facsimile Certificate

I hereby certify that this correspondence is being facsimile transmitted to (703) 872-9089 on the date given below, addressed to M. Alvo, Commissioner for Patents, Washington, DC 20231.

Date:

April 04, 2003


L. James Ristas

Two broad categories of pulp manufacturing techniques are known in the art. The first technique is known as the digestion process, wherein lignocellulose fiber containing material (wood chips) are treated with chemicals and heat in order to break down the structure of the wood chips and produce pulp suitable for use in the paper making process. A second technique for producing pulp, known as the mechanical pulping process, involves passing lignocellulose fiber containing material, such as wood chips, through an attrition device where the fibers of the wood chips are mechanically separated. Variations of the mechanical pulping process are also known and include the thermo-mechanical pulping process ("TMP"). In the TMP process, wood chips are fed into a pressurized pre-heater, treated with steam and are subsequently ground into pulp. U.S. Patent Application No. 08/736,366, filed October 23, 1996, "Low-Resident, High-Temperature, High Speed Chip Refining", (now U.S. Pat. No. 5,776,305) discloses a further variation on the ground wood pulp process, whereby the wood chips are held at a temperature greater than the glass transition temperature (T_g) of the lignin in the wood chips for a period of time preferably less than 30 seconds, then immediately refined in a high speed disc refiner. According to the application, the wood chips are preferably subjected to a preheat environment of saturated steam at an elevated pressure in the range of 75-95 psi. (All values of pressure expressed as psi throughout this Specification including claims, refer to pounds per square inch gage pressure, i.e., psig). [(The assignee of the 08/736,366 application identifies the system and associated process as the "RTS".)]

In the Claims

Amendment of claims 29, 31, and 36 showing [deletions] and additions relative to claims as presented for appeal on 01/21/03:

29. A method for producing thermo-mechanical pulp from lignocellulose fiber-

ANDR/346/US

2